



Pak & Pishro Chemical Co

**Product : Triple Pressed and Rubber Grade Stearic Acid**

Quality Control Data	Pishro Chemical Co.														
	Acid Value Mg KOH/g	Iodine Value % Max	Titer °C	LOV Color		%chain distribution				Sap.value mgKOH/g				Water content %Max	Unsa p %Ma x
				R	Y	c14	c12	c16	c18						
Triple Pressed Stearic acid	206-213	0.5	55-57	0.2	52-55	0-1	0-2	42-64	58-64	206-214	0.2	1			
Rubber Grade Stearic acid	Min196	8.0	Min50	2	min50	0-1	0-2	58-64	42-50	Min196	0.2	1			

