



POLYETHYLENE WAX. Code PE 2576

Characteristic	Result	Test Method
Form	Flake	-
Color	White	-
Viscosity (140°C)/ cSt	23.34	ASTM D 1986
Volatile Matter (Moisture)/ %	8.8	ASTM D 6658
Needle Penetration/ 0.1mm	21	ASTM D 1321
Softening Point/°C	100	ASTM E 28
Melting Point /°C	112	ASTM D 127
Density/ g/cm ³	0.888	ASTM D 1298
Flash Point/°C	143	ASTM D 92