



POLYETHYLENE WAX _Pak Wax 017

Specification		Test method
Appearance	In range	VRM-WI-079-00
Acid number	< 0.1	ASTM D1386-10
Flash point	>180°C	ASTM D92-12B
Penetration index	≤ 5	(d.mm) ASTM D 1321
Water content	None	LABORTORY MANUAL
Softening point	≥100°C	ASTM E28(ring and ball)
Density	0.92-0.94	ASTM D 1505
Mass loss (150°C & 1h)	< 1%	
Viscosity (120°C)	10-30cp	ASTM D3236